

PANAX GREEN GY


Revision Date: 03/2015 Revision No.: 3

PRODUCT DESCRIPTION

Color Index	Pigment Green 7
C.I. No.	74260
Chemical Type	Chlorinated Copper-Phthalocyanine pigment
CAS No.	1328-53-6
EINECS No.	215-524-7

FULL SHADE


REDUCTION 1:25 TiO₂



PHYSICAL DATA

Appearance	Green powder	
pH (2% aqueous)	5-7	ISO 787-9
Specific gravity	2,2 g/cm ³	ISO 787-10
Bulk volume	370 cm ³ /100 g	ISO 787-11
Oil absorption	23 g/100 g	ISO 787-5

CHEMICAL STRUCTURE OF THE PIGMENT


Molecular formular C₃₂H₂Cl₁₅CuN₈
Molecular Mass 1.095 g/mol

FASTNESS PROPERTIES

Acid	5	ISO 787-4
Alkali	5	ISO 787-4
Water	5	ISO 2836
Ethanol	5	ISO 2836
Xylene	5	ISO 2836
MEK	5	ISO 2836
DOP	5	ISO 2836
Heat / 150°C, 10 min	5	ISO 787-21
Heat/ 210°C, 10 min	5	ISO 787-21
Light 1/3 SD	8	ISO 105-B01
Light 1/25 SD	8	ISO 105-B01

APPLICATION RECOMMENDATION

Publication gravure	-
Water base flexo	-
Offset	-
Paint (oil base)	-
Paint (water base)	-
Plastics	recommended

STANDARD PACKAGING

Paper bags	10 kg
Big Bags type C	On request

REGULATORY COMPLIANCE

German BfR IX	-
AP(89)1	-
FDA 21 CFR 178.3297	listed
CONEG, EC 94/62	-
ROHS 2002/95/E, 2005/618/EC	-

Our product specific end application information are based upon our current knowledge. They are presented without any representation or warranty concerning the suitability, performance or correctness of the product for a particular application or use. Significant variations can occur between test results and results obtained in actual use. We strongly advise that the customer test the product in the specific intended application under conditions expected during use.

HEAD-OFFICE

174, Gaejwa Ro, GEUMJEONG-GU
609-845 BUSAN, KOREA
Tel.: +82 51 523 1515
Fax: +82 51 523 7272
Email: trade@ukseung.co.kr
http://www.ukseung.co.kr

EUROPE OFFICE

UK SEUNG Europe GmbH
Hauptstrasse 14
D-63860 Rothenbuch, Germany
Tel. : +49 6094 9897426
Fax: +49 6094 9897427
Email: info@ukseung-europe.de
http://www.ukseung-europe.de